

SILICONIZED EQUIPMENT COATING

General Purpose Release Agent

Form: Liquid

Color: Clear, colorless

Odor: Lemon

pH: No data available

Solubility (in water): Insoluble
(in mineral spirits): Soluble

VOC Content (% by weight): >90.0

Flash Point (Closed Cup): 103°F

Specific Gravity: 0.79 g/ml

Density: 6.50 lbs/gal

Storage Stability (at 70°F): 1 year

<u>Ingredients</u>	<u>C.A.S. #</u>
Distillates (Petroleum), Hydrotreated Light	64742-47-8
Polydimethylsilicone.....	63148-62-9
Mixed Xylenes	1330-20-7
Cumene	98-82-8
Fragrance.....	Mixture

Other Uses...	
•	Conduit Lubricant
•	Brick Protector
•	Wall Coating
•	Graffiti Inhibitor
•	Water Proofer
•	Reflective Sign Coating
•	Asphalt Release Agent
•	Concrete Truck Protector

DIRECTIONS: Apply with a sprayer, paint roller or brush. For best results and longer life, wash equipment thoroughly and allow to dry before applying SILICONIZED EQUIPMENT COATING. Two light coats, allowing one hour of drying time between applications, will provide good protection and prevent unwanted deposits from bonding to the surface.

For maximum protection, apply SILICONIZED EQUIPMENT COATING at the end of each work period. Several applications over summer storage periods will preserve equipment.

HMIS®			NFPA®		
	Severe	4	Extreme		
Health	Serious	3	High	Health.....	2
Flammability.....	Moderate	2	Moderate	Flammability.....	2
Reactivity.....	Slight	1	Slight	Reactivity.....	0
Personal Protection.....	Minimal	0	Insignificant	Special Precautions.....	None