



# CRACK ROLL

## LATEX CONCRETE REPAIR

Use from Featheredge to 1/4" per application  
Yields 40 sq. ft. @ 1/8" for Trowel Applications  
Has Up To 1 Hour Working Time

### DANGER

Causes serious eye damage. Causes skin irritation.  
May cause respiratory irritation. Causes damage to organs  
(Lung) through prolonged or repeated exposure (inhalation).

**KEEP OUT OF REACH OF CHILDREN**

**NET CONTENTS: 52 POUNDS**

**DO NOT ALLOW TO FREEZE**



**DANGER:** Causes serious eye damage. Causes skin irritation. May cause respiratory irritation. Causes damage to organs (Lung) through prolonged or repeated exposure (inhalation).

**PREVENTION:** Wear protective gloves and eye/face protection. Use only outdoors or in a well-ventilated area. Do not breathe dust/gas/mist/vapors. Do not eat, drink or smoke when using this product. Wash with plenty of water and soap thoroughly after handling.

**IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a POISON CENTER or doctor/physician.

**IF ON SKIN (or hair):** Wash with plenty of soap and water. Take off contaminated clothing and wash before reuse.

**STORAGE:** Store in a well-ventilated place. Keep container tightly closed. Store locked up.

**DISPOSAL:** Dispose of contents/ container to hazardous or special waste collection point.

**WARNING:** This product contains a chemical known to the state of California to cause cancer. This product contains a chemical known to the state of California to cause reproductive/developmental effects.

Use from Featheredge to 1/4" per application.

**APPLY TO CLEAN SOUND SUBSTRATES. REMOVE ANY DUST, PAINT, CURING COMPOUNDS AND ANY FOREIGN MATTER FROM SURFACE PRIOR TO USE.**

**AFTER APPLICATION WAIT 6 TO 8 HOURS** (depending on thickness and conditions) **PRIOR TO LIGHT TRAFFIC.**

**MIX WITH LATEX LIQUID ONLY. 1 GALLON INCLUDED.**

#### For Patch or Trowel Applications:

Approximately 1 gallon of Latex Liquid is required to mix 40 lb. of product.

Always add and mix product into liquid. Hold back 1 part latex liquid and adjust for consistency desired. Thorough mixing is required. Mix for 2-3 minutes until an even consistency is obtained. Apply material above 40° F. Rub or scratch mixed material onto surface just prior to application. Coverage will depend on thickness and substrate conditions.

#### FOR BEST RESULTS / LIMITATIONS:

Apply to clean, sound and stable substrates. Do not re-temper already mixed product. Check moisture content (mat test) prior to applying waterproof topping. Product is to be stored in a dry, cool place.

#### INGREDIENTS/CAS#:

Portland cement (65997-15-1);  
Crystalline silica (14808-60-7);

#### NFPA® RATINGS:

Health: 3; Flammability: 0; Reactivity: 0



Please Recycle.

1857.061815

Share Corp. • P.O. Box 245013 • Milwaukee, WI 53224 • (800) 776-7192 • www.sharecorp.com