

# SILICONE RTV - CLEAR

## Sealer – Caulker - Adhesive

**Form:** Aerosol (Solid Paste)

**Color:** Clear

**Odor:** Acetic Acid

**pH:** N/D

**Solubility ( in water):** No data available  
**(in mineral spirits):** No data available

**VOC Content (% by wt):** N/D

**Flash Point (Closed Cup):** >212°F

**Specific Gravity:** 1.007 g/cm<sup>3</sup>

**Density:** 8.40 lbs/gal

**Storage Stability (at 70°F):** 1 year

**Ingredients**

**C.A.S. #**

Triacetoxymethylsilane ..... 17689-77-9  
 Methylsilanetriyl triacetate..... 4253-34-3  
 1,1-Difluoroethane, liquefied,  
 under pressure ..... 75-37-6

Use it to seal...	
•	<b>HVAC Duct Work</b>
•	<b>Plumbing Fixtures</b>
•	<b>Electrical Connections</b>
•	<b>Windows</b>
•	<b>Doors</b>
•	<b>Walls</b>
•	<b>Shower Walls &amp; Tubs</b>
•	<b>Glass</b>

**DIRECTIONS:** Clean and dry surface. Remove oil, grease or soap from surface. Hold can at 45° angle and apply in any direction. Sealant normally “skins over” in 5 minutes and dries tack free to the touch in one hour. If spreading or working material is required, do immediately after applying. Paper towels can be used to remove excess. Sealant cures and bonds fully in 24 hours and maximum strength is achieved in 7 days. For food use sealant must be washed thoroughly before use. Sealant is easily trimmed with a sharp tool. Do not destroy bond by undercutting.

HMIS®			NFPA®		
	Severe	4	Extreme		
Health .....	Serious	3	High	Health.....	1
Flammability .....	Moderate	2	Moderate	Flammability .....	2
Reactivity.....	Slight	1	Slight	Reactivity.....	0
Personal Protection.....	Minimal	0	Insignificant	Special Precautions .....	None